AEM

Lab collaboration with General Office of Standard & Industrial Research of Tehran - No. certification: T/1565

ISIRI-ISO/IEC 17025 - No. certification: NACI/Lab/711

Document code:

F4030/07

Revision date: 94/06/15

								_
2000	Bartar Miran Istitute		Test Report					
Applicant		Ms. Farzaneh	Ms. Farzaneh			1400102516		Licenses: -License of research from the Ministry of Industries and Business - The authority license for
company/producer		Polymer Azin Esf (PJS)	Polymer Azin Esfarayen Co. (PJS)		olished on	2022/03/17		
Sample N	lame and Type	PP melt blown ma	PP melt blown material		Supplement	•		research collaboration with the Ministry of Petroleum -License of Iran Technical and Vocational Training Organization - License for holding workshops for Institute of Standards and Industrial Research of Iran
Trade nar	me	-	-		mpling	-		
Application	on number	-	-		eceived on	2022/01/15		
Application date		2022/01/12	2022/01/12		ested on	2022/03/16		Agreements:
Sample co			-		ı date	-		-Iran Polymer and Petrochemical Institute
Address of applicant: -				Production series		-		- Sazeh Gostar Saipa - Razi Metallurgical Research Center
,				Place of sampling]-		
Tel: +982181444263 Fax: -				Type of standard		-		- Razi foundation - Gostaresh Plastic
Standard Reference: - Cost of experiment:				conditioning:	nditioning: Temperature: 23 =		y: 50 ± 5 %	- Aryanam
No.	Test Measurement		Standard		Acceptance Limit		Result	
1	Ash content		, A	ASTM D5630		-	198 ppm	

Procedure condition:

Ash content: 1hr. at 600°C

Comments:

1- Sampling was done by applicant.

2- These results are valid just for this received sample.

3- Amount of specimen is in accordance with the standard.

CAEMI

Tested by: Sude Bayatani

Technical Manager: Parham Noori

Managing Director: Alireza Mirbolook

Address: 2nd floor, No.1, 25th street, Lashgari Expy, Tehran, Iran. Po. Code: 1399837611 Tel & Fax: +982144539094-5, +982144565305 This report is invalid without logo, sign, seal and hologram sticker's institution. Copy of this paper is not valid and for each test exports only one result.

Page 1 of 1