(ABM)

Andisheh Bartar Miran

Institute

Sample Name and Type

Application number

Address of applicant: -

Tel: +982181444263

Application date

Sample code

company/producer

Applicant

Trade name

Lab collaboration with General Office of Standard & Industrial Research of Tehran - No. certification: T/1565

ISIRI-ISO/IEC 17025 - No. certification: NACI/Lab/711

Test Modified Report

Result Published on

Date of sampling

Sample Received on

Sample Tested on

Production date

Production series

Place of sampling

Type of standard

Appendix/Supplement

Test code

1400102516

2022/02/10

2022/01/15

2022/01/17

Document code: F4030/07

Revision date: 94/06/15

Licenses:
-License of research from the
Ministry of Industries and

Business
- The authority license for research collaboration with the Ministry of Petroleum
- License of Iran Technical and Vocational Training Organization
- License for holding workshops for Institute of Standards and

Agreements:

-Iran Polymer and Petrochemical Institute

Industrial Research of Iran

- Sazeh Gostar Saipa
- Razi Metallurgical Research Center
- Razi foundation
- Gostaresh Plastic - Aryanam

Standard Reference: -		Cost of experiment:		conditioning:	Temperature: 23 ± 2°C	Humidity: $50 \pm 5 \%$	- Aryanam
No.	Test Measurement			Standard		Result	
1	Water absorption		ISO 62		0.03% 300 ppm		

Procedure condition:

Drying temperature and time before immersion: 50°C, 42hr

Fax: -

Test Condition: immersion in Distill Water @ ambient Temperature, 220hr

Ms. Farzaneh

1400/049

2022/01/12

Polymer Azin Esfarayen Co.

PP melt blown material

Drying temperature and time after immersion: 50°C, 18hr

Comments:

1- Sampling was done by applicant.

2- These results are valid just for this received sample.

3- Number of specimens is in accordance with the standard.

Managing Director: Alireza Mirbolook

Tested by: Sude Bayatani

Technical Manager: Parham Noori

Address: 2nd floor, No.1, 25th street, Lashgari Expy, Tehran, Iran. Po. Code: 1399837611 Tel & Fax: +982144539094-5, +982144565305 This report is invalid without logo, sign, seal and hologram sticker's institution. Copy of this paper is not valid and for each test exports only one result.

Page 1 of 1