


		Lab collaboration with General Office of Standard & Industrial Research of Tehran - No. certification: T/1565 ISIRI-ISO/IEC 17025 - No. certification: NACI/Lab/711			Document code: F4030/07 Revision date: 94/06/15
Andisheh Bartar Miran Institute		Test Report			
Applicant	Ms. Farzaneh	Test code	1400102516		
company/producer	Polymer Azin Esfarayen Co. (PJS)	Result Published on	2022/04/20		
Sample Name and Type	PP melt blown material	Appendix/Supplement	-		
Trade name	-	Date of sampling	-		
Application number	1401/004	Sample Received on	2022/01/15		
Application date	2022/04/17	Sample Tested on	2022/04/19		
Sample code	-	Production date	-		
Address of applicant: -		Production series	-		
		Place of sampling	-		
		Type of standard	-		
Tel: +982181444263 Fax: -					
Standard Reference: -	Cost of experiment:.....	conditioning:	Temperature: 23 ± 2°C	Humidity: 50 ± 5 %	
No.	Test Measurement	Standard	Acceptance Limit	Result	
1	Melt Flow Index (MFI)	ASTM D1238	-	1582 gr/10min	
Procedure condition: MFI: Temp. 230°C, weight: 2.16 kg					
Comments: 1- Sampling was done by applicant. 2- This result is valid just for this received sample. 3- Amount of specimen is in accordance with the standard.					
Tested by: Sude Bayatani 		Technical Manager: Parham Noori 		Managing Director: Alireza Mirbolook 	

Licenses:
 -License of research from the Ministry of Industries and Business
 - The authority license for research collaboration with the Ministry of Petroleum
 -License of Iran Technical and Vocational Training Organization
 - License for holding workshops for Institute of Standards and Industrial Research of Iran

Agreements:
 -Iran Polymer and Petrochemical Institute
 - Sazeh Gostar Saipa
 - Razi Metallurgical Research Center
 - Razi foundation
 - Gostaresh Plastic
 - Aryanam



Address: 2nd floor, No.1, 25th street, Lashgari Expy, Tehran, Iran. Po. Code: 1399837611 Tel & Fax: +982144539094-5, +982144565305
 This report is invalid without logo, sign, seal and hologram sticker's institution. Copy of this paper is not valid and for each test exports only one result.